

12

EUROPEAN PATENT APPLICATION

21 Application number: 87304922.5

22 Date of filing: 03.06.87

51 Int. Cl.³: C 08 K 3/28
 C 08 K 3/30, A 61 L 15/00

30 Priority: 04.06.86 JP 130567/86
 03.04.87 JP 83190/87

43 Date of publication of application:
 16.12.87 Bulletin 87/51

64 Designated Contracting States:
 BE DE ES FR GB IT NL SE

71 Applicant: SEITETSU KAGAKU CO., LTD.
 346-1, Miyanishi Harimacho, Kako-gun
 Hyogo-ken 673-01(JP)

72 Inventor: Obayashi, Shigeji
 31-2, Matsugasaki 3-chome
 Akashi-shi Hyogo-ken(JP)

73 Inventor: Nakamura, Morio
 6-12, Miyakodai 3-chome Kamisho-cho
 Kakogawa-shi Hyogo-ken(JP)

74 Inventor: Yamamoto, Takushi
 1044, Imazaite Shikama-ku
 Himeji-shi Hyogo-ken(JP)

75 Inventor: Tanaka, Hitoshi
 1044, Imazaite Shikama-ku
 Himeji-shi Hyogo-ken(JP)

76 Inventor: Sakamoto, Yuji
 1044, Imazaite Shikama-ku
 Himeji-shi Hyogo-ken(JP)

77 Representative: Armitage, Ian Michael et al.
 MEWBURN ELLIS & CO. 2/3 Cursitor Street
 London EC4A 1BQ(GB)

54 Water-absorbent resin composition.

57 A water-absorbent resin composition having superior gel stability comprises a water-absorbent resin, at least one oxygen-containing reducing inorganic salt and, optionally, at least one organic antioxidant

EP 0 249 391 A2

WATER-ABSORBENT RESIN COMPOSITION

The present invention relates to a water-absorbent
5 resin composition. More particularly, it relates to a
water-absorbent resin composition having an improved
stability to body fluids such as urine, catamenial blood,
secretions and the like, and further relates to a water-
absorbent resin composition having an improved stability to
10 an aqueous solution containing an electrolyte in addition to
an improved stability to body fluids.

Recently, various water-absorbent resins have been
15 developed (for example, see U.S. Patent No. 4,340,706, U.S.
Patent No. 4,093,776, U.S. Patent No. 4,459,396, U.S. Patent
3,980,663 and U.S. Patent No. 4,552,938) and have been
extensively used in various water-absorbent articles such as
diaper, menstrual articles and the like. Thereby,
20 properties of water-absorbent articles are improved. For
example, liquid retention characteristics are improved and
liquid leak is diminished. Further, a comfortable feeling
in wearing water-absorbent article which has absorbed body
fluids is achieved. Accordingly, such a water-absorbent
25 article tends to be kept on for a longer period of time.

On the other hand, it has been found that a gel

resulted from absorption of fluids such as urine, catamenial blood, secretions and the like by a water-absorbent article is crumbled to be out of shape because, in general, a water-absorbent resin of the gel is decomposed by the body fluids
5 with time. Accordingly, as a period of time for keeping a water-absorbent article on becomes longer, liquid retention characteristics of the article are lowered, which results in increase in liquid leak, impairment of feeling in wearing the article and the like. In view of this, it is required
10 to develop a water-absorbent resin which has an improved gel stability to the body fluids.

As a means for improving a gel stability, for example, increase in crosslinking density of a water-absorbent resin may be employed. However, as crosslinking
15 density becomes higher, a water-absorption capacity becomes lower and therefore it is necessary to increase an amount of the resin to be used. This is less economical and causes such a disadvantage that properties of a water-absorbent article are adversely affected.

20

Under these circumstances, the present inventors have studied intensively to obtain a water-absorbent resin having an improved gel stability to the body fluids. As a
25 result, it has been found that the gel stability of a water-absorbent resin to body fluids can be sufficiently

improved without the above disadvantages by incorporation of an oxygen-containing reducing inorganic salt. Further, it has been found that, in addition to gel stability to the body fluids, gel stability of a water-absorbent resin to an aqueous solution containing an electrolyte can be also sufficiently improved while maintaining its high water-absorption capacity by incorporation with an organic antioxidant together with the oxygen-containing reducing inorganic salt.

10 That is, the present invention desirably provides a water-absorbent resin composition having an improved gel stability to the body fluids which is suitable for water-absorbent articles.

 The present invention also desirably
15 provides a water-absorbent resin composition having an improved gel stability to an aqueous solution containing an electrolyte as well as to the body fluids which is suitable for water-absorbent articles.

20

 In one aspect of the present invention, there is
25 provided a water-absorbent resin composition which comprises a water-absorbent resin and at least one oxygen-containing

reducing inorganic salt. This water-absorbent resin composition of the present invention has an improved gel stability to body fluids such as urine, catamenial blood, secretions and the like.

5 In another aspect of the present invention, there is provided a water-absorbent resin composition which comprises a water-absorbent resin, at least one oxygen-containing reducing inorganic salt and at least one organic antioxi-
10 dant. This water-absorbent composition of the present invention has an improved stability to an aqueous solution containing an electrolyte in addition to an improved stability to the body fluids.

In the present invention, although an account of the mechanism of the oxygen-containing reducing inorganic
15 salt and the organic antioxidant in the water-absorbent resin composition is unclear, properties of water-absorbent articles can be remarkably improved simply by incorporation of a small amount of these materials to the water-absorbent resin without any sanitary problem.

20 By using the composition of the present invention, there can be obtained various water-absorbent articles having improved properties such as improved liquid retention characteristics with good prevention of liquid leak and impairment of a feeling in wearing the article. Further,
25 the composition of the present invention can be broadly used in the field where an aqueous solution containing an

electrolyte is involved.

The water-absorbent resin used in the composition
5 of the present invention is not limited to a specific one
and any conventional water-absorbent resin can be used.
Examples of the water-absorbent resin include crosslinked
polyacrylic acid salts, crosslinked copolymers of vinyl
alcohol-acrylic acid salt, crosslinked saponification
10 products of starch-acrylonitrile graft copolymer,
crosslinked starch-acrylic acid salt copolymer, crosslinked
products of polyvinyl alcohol grafted with maleic anhydride,
crosslinked carboxymethyl cellulose alkali metal salt and
the like.

15 In one aspect of the present invention, the water-
absorbent resin is incorporated with the oxygen-containing
reducing inorganic salt to improve its gel stability to body
fluids such as urine, catamenial blood, secretions, etc.

As the oxygen-containing reducing inorganic salt in
20 the present invention, particularly, there can be used at
least one member selected from the group consisting of
sulfites, bisulfites, pyrosulfites, dithionites,
trithionates, tetrathionates, thiosulfates and nitrites.
Specific examples of these oxygen-containing reducing
25 inorganic salts include sulfites such as sodium sulfite,
potassium sulfite, calcium sulfite, zinc sulfite, ammonium

sulfite, etc.; bisulfites such as sodium bisulfite, potassium bisulfite, calcium bisulfite, ammonium bisulfite, etc.; pyrosulfites such as sodium pyrosulfite, potassium pyrosulfite, ammonium pyrosulfite, etc.; dithionites such as
5 sodium dithionite, potassium dithionite, ammonium dithionite, calcium dithionite, zinc dithionite, etc.; trithionates such as potassium trithionate, sodium trithionate, etc.; tetrathionates such as potassium tetrathionate, sodium tetrathionate, etc.; thiosulfates such
10 as sodium thiosulfate, potassium thiosulfate, ammonium thiosulfate, etc.; and nitrites such as sodium nitrite, potassium nitrite, calcium nitrite, zinc nitrite, etc. They can be used alone or in combination thereof. Among them, from the sanitary and gel stability points of view, sodium
15 sulfite, sodium bisulfite, sodium pyrosulfite, sodium dithionite and sodium nitrite are preferred.

In the present invention, the oxygen-containing reducing inorganic salt is used in an amount of 0.001 to 10 parts by weight, preferably, 0.01 to 5 parts by weight per
20 100 parts by weight of the water-absorbent resin. When the amount of the reducing inorganic salt is less than 0.001 part by weight per 100 parts by weight of the water-absorbent resin, improvement of gel stability of the water-absorbent resin to the body fluids is scarcely expected. On
25 the other hand, when the amount is more than 10 parts by weight, a water-absorption capacity of a resulting

composition is lowered, while gel stability of the water-absorbent resin to the body fluids is improved.

In another aspect of the present invention, the water-absorbent resin is incorporated with both the oxygen-
5 containing reducing agent and the organic antioxidant to improve its gel stability to both the body fluids and an aqueous solution containing an electrolyte such as physiological saline solution, artificial urine and the like.

10 In this aspect, the above-described oxygen-containing reducing agent can be used in an amount of the same range as described above in view of gel stability and a water-absorption capacity.

As the organic antioxidant, particularly, there can
15 be used at least one member selected from the group consisting of ascorbic acid and its derivatives, gallic acid and its derivatives, benzothiazoles, dithionates, thiurams, benzimidazoles, formaldehyde sulfoxylates and phenothiazines. Specific examples of these organic
20 antioxidant include ascorbic acid and its derivatives such as L-ascorbic acid, sodium L-ascorbate, isoascorbic acid, sodium isoascorbate, etc.; gallic acid and its derivatives such as gallic acid, methyl gallate, ethyl gallate, n-propyl gallate, isoamyl gallate, octyl gallate, lauryl gallate,
25 etc.; benzothiazoles such as mercaptobenzothiazole, sodium mercaptobenzothiazole, zinc mercaptobenzothiazole, etc.;

dithionates such as zinc methyldithiocarbamate, zinc diethyldithiocarbamate, zinc di-n-butyldithiocarbamate, zinc ethylphenyldithiocarbamate, etc.; thiurams such as tetramethylthiuram disulfide, tetraethylthiuram sulfide, 5 tetrabutylthiuram disulfide, tetramethylthiuram monosulfide, etc.; benzimidazoles such as 2-mercaptobenzimidazole, etc.; formaldehyde sulfoxylates such as sodium formaldehyde sulfoxylate, etc.; and phenothiazines such as phenothiazine, 2-methoxyphenothiazine, etc. They can be used alone or in 10 combination thereof. Among them, from the sanitary and gel stability points of view, L-ascorbic acid, sodium L-ascorbate, isoascorbic acid, sodium isoascorbate and n-propyl gallate are preferred.

In the present invention, the organic antioxidant 15 is used in an amount of 0.0001 to 10 parts by weight, preferably, 0.001 to 5 parts by weight per 100 parts by weight of the water-absorbent resin. When the amount of the antioxidant is less than 0.0001 part by weight per 100 parts by weight of the water-absorbent resin, improvement of gel 20 stability of the water-absorbent resin to an aqueous solution containing an electrolyte such as physiological saline solution or artificial urine is insufficient. On the other hand, when the amount is more than 10 parts by weight, gel stability of the water-absorbent resin becomes 25 inferior. Further, when the water-absorbent resin is incorporated with only the antioxidant without incorporation

of the oxygen-containing reducing inorganic salt, gel stability of the water-absorbent resin is rather lowered and therefore, in the present invention, the antioxidant should be used together with the inorganic salt.

5 The water-absorbent resin composition of the present invention can be prepared by blending the water-absorbent resin with the oxygen-containing reducing inorganic salt and, if necessary, the organic antioxidant. The blending method is not limited to specific one and any
10 known method can be employed. For example, the inorganic salt and the antioxidant can be added to a polymerization reaction mixture of the water-absorbent resin. Further, they can be blended with the dried water-absorbent resin by so-called dry blending.

15 The water-absorbent resin composition of the present invention can be used for the production of various water-absorbent articles according to a conventional method.

 The following Preparations, Comparative Examples and Examples further illustrate the present invention in
20 detail but are not to be construed to limit the scope thereof.

PREPARATIONS

Preparation 1

25 Cyclohexane (213 g) was placed in a 500 ml four necked round bottom flask equipped with a stirrer, a reflux

condenser, a dropping funnel and a nitrogen gas inlet. To the flask was charged sorbitan monolaurate having HLB of 8.6 (manufactured and sold by Nippon Oil and Fats Co., Ltd., Japan under the trade name of Nonion LP-20R)(1.9 g). After
5 dissolution of the surfactant with stirring at room temperature, dissolved oxygen was purged with nitrogen gas.

Separately, a 80% (w/w) aqueous solution of acrylic acid (48.8 g) was placed in a 200 ml conical flask and a 25.9% (w/w) aqueous solution of sodium hydroxide (66.7 g)
10 was added dropwise with cooling to neutralize 80 mole % of the acrylic acid. To the mixture was added potassium persulfate (0.13 g).

The resulting partially neutralized acrylic acid solution was added to the above four necked round bottom
15 flask and the mixture was thoroughly purged with nitrogen gas. The mixture was heated and subjected to polymerization reaction for 3 hours while maintaining the bath temperature at 55 to 60°C.

Water and cyclohexane were distilled off and the
20 residue was dried to obtain a fine granular water-absorbent resin (48.5 g).

Preparation 2

n-Heptane (280 ml) was placed in a 500 ml four necked round bottom flask equipped with a stirrer, a reflux
25 condenser, a dropping funnel and a nitrogen gas inlet. To the flask was charged hexaglyceryl monobehenirate having HLB

of 13.1 (manufactured and sold by Nippon Oil and Fats, Co., Ltd., Japan under the trade name of Nonion GV-106)(0.75 g). After dispersion of the surfactant, dissolved oxygen was purged with nitrogen gas. Temperature was raised to
5 50°C to dissolve the surfactant and then the mixture was cooled to 30°C.

Separately, a 80% (w/w) aqueous solution of acrylic acid (37.5 g) was placed in a 200 ml conical flask and a 25.4% (w/w) aqueous solution of sodium hydroxide (49.3 g)
10 was added dropwise with ice-cooling to neutralize 75 mole % of the acrylic acid. To the mixture was added potassium persulfate (0.045 g).

The resulting partially neutralized acrylic acid solution was added to the above four necked round bottom
15 flask and the mixture was thoroughly purged with nitrogen gas. The mixture was heated and subjected to polymerization reaction for 2 hours while maintaining the bath temperature at 55 to 60°C.

Water and n-heptane were distilled off and the
20 residue was dried to obtain a water-absorbent resin (40.2 g).

Preparation 3

A water-absorbent resin (40.3 g) was obtained according to the same manner as described in Preparation 2
25 except that ethylene glycol diglycidyl ether (0.038 g) was added to the polymerization reaction mixture.

COMPARATIVE EXAMPLES AND EXAMPLES

In the following Comparative Examples and Examples, absorbency, evaluation of gel stability to a saline solution (0.9% (w/w) aqueous solution of sodium chloride),

- 5 preparation of an absorbent article and evaluation of gel stability to human urine were carried out as follows.

Absorbency

A water-absorbent resin (1 g) was dispersed in a 0.9% (w/w) aqueous solution of sodium chloride (200 ml) to 10 thoroughly swell. After 4 hours or 15 hours, the swollen resin was filtered through a 100 mesh metallic wire gauze and the volume of the swollen resin obtained as a filter cake was measured and the value was taken as the absorbency.

Evaluation of gel stability to a saline solution

- 15 The swollen resin obtained in the above measurement of the absorbency was pressed with the fingers to organoleptically evaluate its gel stability according to the following four criteria.

- A: Gel was not crumbled even by pressing strongly.
20 B: Gel was crumbled by pressing strongly.
C: Gel was observed but readily crumbled.
D: No gel form was retained.

Preparation of an absorbent article

A pulp having the basis weight of 150 g/m² was cut 25 out to form a sheet (20 cm x 10 cm) and a water-absorbent

resin or a water-absorbent resin composition (3 g) was uniformly scattered thereon. Further, the same sheet as described above was laminated thereon and pressed by uniformly applying a pressure of 1 kg/cm^2 to obtain an
5 absorbent article.

Evaluation of gel stability to human urine

Human urine (120 ml) was poured on the center part of the above-prepared absorbent article over 1 minute and the article was allowed to stand for 5 minutes. Then, the
10 absorbent article which absorbed human urine was packaged in a polyethylene bag and the bag was placed in an incubator at 37°C . After 4 hours or 15 hours, the absorbent article was taken out of the bag and pressed with the fingers to organoleptically evaluate its gel stability according to the
15 following four criteria.

- A: Gel was not crumbled even by pressing strongly.
- B: Gel was crumbled by pressing strongly.
- C: Gel was observed but readily crumbled.
- D: No gel form was retained.

20 Comparative Examples 1 to 5

By using the water-absorbent resins obtained in the above Preparations 1 to 3 and commercially available water-absorbent resins, Arasorb 720 (crosslinked polyacrylic acid salt manufactured and sold by Arakawa Chemical Co., Ltd.,
25 Japan) and Sanwet IM-1000 (crosslinked starch-acrylic acid salt graft copolymer manufactured and sold by Sanyo Chemical

Industries Co., Ltd., Japan), the above measurement of absorbency, evaluation of gel stability to a saline solution, and evaluation of gel stability to human urine were carried out. The results are shown in Table 1.

Comparative Example 6

A water-absorbent resin composition was prepared by thoroughly blending the water-absorbent resin power (40.0 g) obtained in the above Preparation 2 with L-ascorbic acid powder (0.4 g). By using the water-absorbent resin composition, the above measurement of absorbency, evaluation of gel stability to a saline solution, and evaluation of gel stability to human urine were carried out. However, no desired result could be obtained.

0249391

Table 1

Comp. Ex. No.	Water- absorbent resin	Absorbency (g/g)		Evaluation of gel stability			
		Aqueous 0.9% NaCl		Aqueous 0.9% NaCl		Human urine	
		4 hrs.	15 hrs.	4 hrs.	15 hrs.	4 hrs.	15 hrs.
1	Prep. 1	85	85	B	B	D	D
2	Prep. 2	70	70	A	A	C	D
3	Prep. 3	50	50	A	A	B	C
4	Arasorb 720	62	62	B	B	C	D
5	Sanwet IM-1000	75	75	B	B	D	D

Examples 1 to 24

Various water-absorbent resin compositions were prepared by thoroughly blending the water-absorbent resins used in the above Comparative Examples with oxygen-
5 containing reducing inorganic salts in various ratios. By using the water-absorbent resin compositions thus obtained, the above measurement of absorbency, evaluation of gel stability to a saline solution, and evaluation of gel stability to human urine were carried out. The results are
10 shown in Tables 2A and 2B.

Example 25

A water-absorbent resin composition (40.5 g) was obtained by addition of sodium sulfite (0.4 g) to the polymerization mixture of the above Preparation 2. By using
15 the water-absorbent resin composition thus obtained, the above evaluation of gel stability to human urine was carried out. As the result, both evaluations after 4 hours and 15 hours were A.

Table 2A

Ex. No.	Water-absorbent resin composition		
	Water-absorbent resin	Oxygen-containing reducing inorganic salt	
		Salt	Amount* (parts)
1	Prep. 1	sodium sulfite	0.5
2	Prep. 1	sodium dithionite	1.5
3	Prep. 1	potassium nitrite	4.0
4	Prep. 1	potassium pyrosulfite	1.5
5	Prep. 1	sodium bisulfite	4.0
6	Prep. 2	potassium bisulfite	0.5
7	Prep. 2	sodium nitrite	4.5
8	Prep. 2	calcium nitrite	5.0
9	Prep. 2	sodium pyrosulfite	2.0
10	Prep. 2	potassium bisulfite	0.1
11	Prep. 3	sodium bisulfite	1.0
12	Arasorb 720	potassium sulfite	0.5
13	Arasorb 720	sodium dithionite	3.5
14	Sanwet IM-1000	sodium sulfite	0.05
15	Sanwet IM-1000	sodium sulfite	1.0
16	Sanwet IM-1000	sodium sulfite	5.0
17	Prep. 1	potassium bisulfite	5.0
18	Prep. 1	sodium dithionite	1.5
19	Prep. 2	sodium sulfite	4.0
20	Prep. 2	calcium nitrite	0.5

Table 2A (continued)

Ex. No.	Water-absorbent resin composition		
	Water-absorbent resin	Oxygen-containing reducing inorganic salt Salt	Amount* (parts)
21	Prep. 3	sodium pyrosulfite	1.0
22	Prep. 3	sodium bisulfite	0.1
23	Arasorb 720	sodium sulfite	3.5
24	Sanwet IM-1000	sodium sulfite	2.0

Note: * parts by weight per 100 parts by weight of the water-absorbent resin

Table 2B

Ex. No.	Absorbency** (g/g)		Evaluation of gel stability			
	Aqueous 0.9% NaCl		Aqueous 0.9% NaCl		Human urine	
	4 hrs.	15 hrs.	4 hrs.	15 hrs.	4 hrs.	15 hrs.
1	-	-	-	-	A	B
2	-	-	-	-	A	A
3	-	-	-	-	A	A
4	-	-	-	-	A	A
5	-	-	-	-	A	A
6	-	-	-	-	A	A
7	-	-	-	-	A	A
8	-	-	-	-	A	A
9	-	-	-	-	A	A
10	-	-	-	-	A	B
11	-	-	-	-	A	A
12	-	-	-	-	A	B
13	-	-	-	-	A	A
14	-	-	-	-	B	C
15	-	-	-	-	B	B
16	-	-	-	-	A	A
17	96	32	C	D	A	A
18	120	76	C	D	A	A
19	78	99	B	D	A	A
20	106	53	C	D	A	B

Table 2B (continued)

Ex. No.	Absorbency** (g/g)		Evaluation of gel stability			
	Aqueous 0.9% NaCl		Aqueous 0.9% NaCl		Human urine	
	4 hrs.	15 hrs.	4 hrs.	15 hrs.	4 hrs.	15 hrs.
21	103	47	C	D	A	A
22	55	118	A	C	A	B
23	71	95	A	C	A	A
24	87	120	B	C	A	A

Note: ** variance in absorbency is larger, gel is more unstable.

Examples 26 to 38

Various water-absorbent resin compositions were prepared by thoroughly blending the water-absorbent resins used in the above Comparative Examples with oxygen-
5 containing reducing inorganic salts and organic antioxidants in various ratios. By using the water-absorbent resin compositions thus obtained, the above measurement of absorbency, evaluation of gel stability to a saline solution, and evaluation of gel stability to human urine
10 were carried out. The results are shown in Tables 3A and 3B.

Table 3A

Ex. No.	Water absorbent resin	Water-absorbent resin composition			
		Oxygen-containing reducing inorganic salt		Organic antioxidant	
		Salt	Amount* (parts)	Compound	Amount* (parts)
26	Prep. 1	potassium bisulfite	5.0	L-ascorbic acid	0.002
27	Prep. 1	sodium sulfite	1.0	L-ascorbic acid	0.02
28	Prep. 1	ammonium pyrosulfite	2.8	zinc ethyl- phenyldithio- carbamate	1.3
29	Prep. 2	sodium sulfite	4.0	phenothiazine	0.8
30	Prep. 2	sodium sulfite	1.0	n-propyl gallate	5.0
31	Prep. 2	calcium nitrite	0.5	n-propyl gallate	1.0
32	Prep. 2	calcium nitrite	4.7	n-propyl gallate	1.0
33	Prep. 3	sodium pyrosulfite	1.0	mercapto- benzothi- azole	0.3
34	Prep. 3	sodium bisulfite	0.1	2-mercapto- benzimidazole	0.1
35	Arasorb 720	potassium sulfite	3.5	tetramethyl- thiuram disulfide	3.0
36	Arasorb 720	sodium dithionite	1.1	sodium formaldehyde sulfoxylate	4.8

0249391

Table 3A (continued)

Ex. No.	Water-absorbent resin composition				
	Water absorbent resin	Oxygen-containing reducing inorganic salt	Organic antioxidant		
		Salt	Amount * (parts)	Compound	Amount * (parts)
37	Sanwet IM-1000	sodium sulfite	2.0	sodium isoascorbate	0.005
38	Sanwet IM-1000	sodium sulfite	2.0	sodium isoascorbate	0.1

Note: * parts by weight per 100 parts by weight of the water-absorbent resin

Table 3B

Ex. No.	Absorbency** (g/g)		Evaluation of gel stability			
	Aqueous 0.9% NaCl		Aqueous 0.9% NaCl		Human urine	
	4 hrs.	15 hrs.	4 hrs.	15 hrs.	4 hrs.	15 hrs.
26	83	83	B	B	A	A
27	84	84	B	B	A	A
28	85	85	B	B	A	A
29	68	68	A	A	A	A
30	69	70	A	A	A	A
31	70	70	A	A	A	A
32	67	66	A	A	A	A
33	50	50	A	A	A	A
34	50	50	A	A	A	A
35	58	57	A	A	A	A
36	59	59	A	A	A	A
37	74	74	B	B	A	A
38	74	74	B	B	A	A

Note: ** variance in absorbency is larger, gel is more unstable.

As seen from Tables 1, 2A and 2B, the water-
absorbent resin composition of the present invention
comprising the water-absorbent resin and the oxygen-
containing reducing inorganic salt has superior gel
5 stability to the body fluid in comparison with the water
absorbent resin alone. Further, as seen from Table 1, 3A
and 3B, the water-absorbent resin composition of the present
invention comprising the water-absorbent resin, the oxygen-
containing reducing inorganic salt and the organic
10 antioxidant has superior gel stability to both the body
fluid and an aqueous solution containing an electrolyte in
comparison with the water absorbent resin alone.

CLAIMS

1. A water-absorbent resin composition which comprises a water-absorbent resin and at least one oxygen-containing
5 reducing inorganic salt.
2. A water-absorbent resin composition according to claim 1, wherein the oxygen-containing reducing inorganic salt is at least one sulfite, bisulfite, pyrosulfite, dithionite,
10 trithionate, tetrathionate, thiosulfate, nitrite or a mixture thereof.
3. A water-absorbent resin composition according to claim 1 or claim 2, wherein the composition contains the oxygen-
15 containing reducing inorganic salt in an amount of 0.001 to 10 parts by weight per 100 parts by weight of the water-absorbent resin.
4. A water-absorbent resin composition which comprises a
20 water-absorbent resin, at least one oxygen-containing reducing inorganic salt and at least one organic antioxidant.
5. A water-absorbant resin composition according to claim 4, wherein the oxygen-containing reducing inorganic salt is
25 at least one sulfite, bisulfite, pyrosulfite, dithionite, trithionate, tetrathionate, thiosulfate, nitrite, or a

mixture thereof.

6. A water-absorbent resin composition according to claim 4 or claim 5, wherein the composition contains the oxygen-
5 containing reducing inorganic salt in an amount of 0.001 to 10 parts by weight per 100 parts by weight of the water-absorbent resin.

7. A water-absorbent resin composition according to any
10 one of claims 4 to 6, wherein the organic antioxidant is at least one of ascorbic acid and its derivatives, gallic acid and its derivatives, benzothiazoles, dithionates, thiurams, benzimidazoles, formaldehyde sulfoxylates and phenothiazines.

15 8. A water-absorbent resin composition according to any one of claims 4 to 7, wherein the composition contains the organic antioxidant in an amount of 0.0001 to 10 parts by weight per 100 parts by weight of the water-absorbent resin.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 249 391
A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 87304922.5

(22) Date of filing: 03.06.87

(51) Int. Cl.³: C 08 K 3/28
C 08 K 3/30, A 61 L 15/00

(30) Priority: 04.06.86 JP 130567/86
03.04.87 JP 83190/87

(41) Date of publication of application:
16.12.87 Bulletin 87/51

(42) Date of deferred publication of search report 27.09.89

(44) Designated Contracting States
BE DE ES FR GB IT NL SE

(71) Applicant: SEITETSU KAGAKU CO., LTD.
348-1, Miyanishi Harimacho, Kako-gun
Hyogo-ken 673-01(JP)

(72) Inventor: Obayashi, Shigeji
31-2, Matsugaoko 3-chome
Akashi-shi Hyogo-ken(JP)

(72) Inventor: Nakamura, Morio
6-12, Miyakodai 3-chome Kamisho-cho
Kakogawa-shi Hyogo-ken(JP)

(72) Inventor: Yamamoto, Takushi
1044, Imazaiki Shikama-ku
Himeji-shi Hyogo-ken(JP)

(72) Inventor: Tanaka, Hitoshi
1044, Imazaiki Shikama-ku
Himeji-shi Hyogo-ken(JP)

(72) Inventor: Sakamoto, Yuji
1044, Imazaiki Shikama-ku
Himeji-shi Hyogo-ken(JP)

(74) Representative: Armitage, Ian Michael et al.
MEWBURN ELLIS & CO. 2/3 Cursitor Street
London EC4A 1BQ(GB)

(54) Water-absorbent resin composition.

(57) A water-absorbent resin composition having superior gel stability comprises a water-absorbent resin, at least one oxygen-containing reducing inorganic salt and, optionally at least one organic antioxidant

0 249 391 A3



European Patent
Office

EUROPEAN SEARCH REPORT

0249391

Application Number

EP 87 30 4922

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
10	A	US-A-4 500 670 (M. McKINLEY et al.) * Claims; column 2, lines 55-66 *	1-8
			C 08 K 3/28 C 08 K 3/30 A 61 L 15/00
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			C 08 K C 08 L A 61 L
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
THE HAGUE		30-06-1989	HOFFMANN K.W.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosures P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons A : member of the same patent family, corresponding document	

EP Form 1501 01 81 (P. 001)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ BLACK BORDERS

☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☐ FADED TEXT OR DRAWING

☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☐ SKEWED/SLANTED IMAGES

☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☐ LINES OR MARKS ON ORIGINAL DOCUMENT

☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)